



1-PART EPOXY ACRYLIC CONCRETE & GARAGE FLOOR PAINT

NO. 900



PRODUCT INFORMATION

A high-performance, ready-to-use, single component water-based floor paint that resists hot tire pick-up and marring. The finish is resistant to household type chemicals, oil and gasoline, which reduces the need for maintenance of hard-to-clean interior or exterior floors. This durable, satin finish floor paint also resists scuffing, fading, cracking, peeling and blistering.

RECOMMENDED USES:

Properly prepared interior or exterior surfaces such as:

- Concrete

Ideal for horizontal surfaces such as: Garage Floors, Driveways, Basements and Porches. DO NOT use on vertical surfaces or areas subject to hydrostatic pressure. NOT for industrial use. DO NOT use on areas subject to fork-lifts.

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load:

No. 900 122 oz. / 8 oz.

No. 930 116 oz. / 14 oz.

Pre-Mixed Colors:

No. 901 Silver Gray

No. 902 Slate Gray

Gloss: 15-25 @ 60°

Sheen: 40-60 @ 85°

Resin Type: Epoxy/Acrylic

Weight per Gallon: 9.7lbs.

% Solids by Volume: 30.0%

% Solids by Weight: 39.7%

VOC: <50 g/L

Flash Point: N/A

Viscosity: 90-100 KU

Recommended Film Thickness:

Wet: 5.3 Dry: 1.6 mils @ 300 Sq. Ft./Gal.

Wet: 3.2 Dry: 1.0 mils @ 500 Sq. Ft./Gal.

Coverage: 300-500 Sq. Ft./Gal. depending on application method and substrate porosity. Does not include the loss of material from spraying.

APPLICATION:

Brush: Nylon/polyester

Roller: 3/8"-1/2" nap

Spray: .015"-.019"

Filter: 60 mesh

Thinning: Do Not Thin.

Dry Time: @ 77° & 50% RH

Longer dry time may be required in cooler temperatures and higher humidity.

To Touch: 1 hour

To Recoat: 4 to 6 hours

Allow surface to dry 24-48 hours before subjecting painted surface to heavy foot traffic.

Allow 7 days before subjecting painted surface to automobile traffic.

SURFACE PREPARATION:

New and Uncoated Concrete or Masonry Surfaces:

New concrete must cure for a minimum of 30 days. For proper penetration and adhesion of topcoat, use a product such as muriatic acid to clean and etch the surface. Follow all label instructions. Apply a product such as BEHR PREMIUM® Concrete & Masonry Bonding Primer No. 880 to increase adhesion of topcoat to the surface. Follow all label instructions.

Painted, Stained or Sealed Concrete:

Option 1- To completely remove any previous coating or sealer. Follow all label instructions.

Option 2- To recoat over an existing coating, remove any loose or peeling paint and scuff sand the surface. Clean previously coated surfaces in sound condition. Clean and etch any bare concrete area. Follow all label instructions. Spot prime all bare concrete areas with a product such as BEHR PREMIUM Concrete & Masonry Bonding Primer No. 880 to increase adhesion of topcoat to the surface. Follow all label instructions.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the National Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead.

COMPLIES WITH THE BELOW AS OF 9/1/2014

SCAQMD	YES	AIM	YES
CARB	YES	LEED v.3 (2009) [†]	YES
OTC	YES	FLAME SPREAD/CLASS A	YES
LADCO	YES		

[†]Please visit www.usgbc.org/LEED for additional details.

CLEAN UP:

Clean all tools and equipment with clean water. For disposal of empty containers and unused product, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying too fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered too hot to apply this coating.
- Avoid heavy traffic for 72 hours.
- DO NOT APPLY MORE THAN TWO COATS
- Allow 30 days before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

GENERAL INFORMATION:



Warning! Causes eye and skin irritation. Wear protective clothing, gloves, eye, and face protection. Do not eat, drink, or smoke when using this product. Take off contaminated clothing and wash it before reuse. Wash hands thoroughly after handling. Dispose of unused, contents, container and other contaminated wastes in accordance with local, state, federal and provincial regulations.

First aid: If in eyes: Rinse cautiously with water for several minutes and remove contacts if present and easy to do. Continue rinsing and get medical attention if eye irritation persists. **If on skin:** Wash with plenty of soap and water. **If swallowed:** Rinse mouth and get medical attention if you feel unwell.